

Si₃N₄ Bonded SiC Bricks

Composition

SiC	≥ 72.0
Si ₃ N ₄	≥ 21.0
Fe ₂ O ₃	≤ 0.3
Si	≤ 0.3
Apparent Porosity (%)	≥ 16.0
Bulk Density (g/cm ³)	≥ 2.68



Compressive Strength (Mpa)	Room temperature	≥ 180.0
Bending Strength (Mpa)	Room temperature	≥ 45.0
	1400°C	≥ 55.0
Thermal Conductivity (W/m-K)	650°C	18.5
	1000°C	16.0
Thermal Diffusivity (cm ² /s)	650°C	0.064
	1000°C	0.053
Linear Expansion	30°C - 1100°C	4.02 x 10 ⁻⁶ (k ⁻¹)
	30°C - 1100°C	4.06 x 10 ⁻⁶ (k ⁻¹)

Applications

Aluminum Electrolytic Cell
Chemical Reaction Pots
High Temperature Furnaces
Piping for Aluminum Transport

NOTE: The information contained in this bulletin is believed to be accurate and reliable but is not to be construed as implying any warranty or guarantee of performance. Data are subject to reasonable variations and should not be used for specification purposes.

Trademarks

Registered trademarks contained in this document are owned by Knight Material Technologies in the United States and may be registered in other jurisdiction, unless otherwise stated. Refer to our website for trademark details: www.knightmaterials.com.

©2021 Knight Material Technologies - All Rights Reserved

5385 Orchard View Drive S.E. · P.O. Box 30070
East Canton, Ohio USA 44730
Phone: +1 (330) 488-1651
Email: sales@knightmaterials.com
www.knightmaterials.com