

DURO™ TYPE II-E Acid Resistant Brick

ACID RESISTANT FIRECLAY BRICK

DURO™ Type II-E Acid Proof Brick meet ASTM Specification C 279 Type II for acid-proof masonry. DURO Brick are available in many more sizes and shapes than red shale brick, making them more adaptable to acid resistant masonry construction of various size vessels and dished heads.

All DURO Brick are true refractory, and therefore, are preferred for corrosion resistant work at high temperatures, in contrast to red shale products

TYPICAL PHYSICAL DATA

Water Absorption	7%	7%
Density	132.0 lb/ft ³	2,115 kg/m ³
Acid Solubility	3%	3%
Compressive Strength	21,600 psi	150 MPa
Modulus of Rupture	2,890 psi	20 MPa
Tensile Strength	1,200 psi	8.3 MPa
Young's Modulus	9.2*10 ⁶ psi	6.3*10 ⁴ MPa
Coefficient Thermal Expansion	2.6*10 ⁻⁶ in/in/°F	4.7*10 ⁻⁶ mm/mm/°C
Thermal Conductivity	8.0 BTU/in/hr-ft ² -°F	1.2 W/M-K
Poisson's Ratio	0.27	0.27

**The above physical data was derive by using ASTM Test Specifications C-20, C-133, C-279 and C-885*

TYPICAL CHEMICAL DATA

WEIGHT

Alumina	Al ₂ O ₃	28.7%
Silica	SiO ₂	63.8%
Titania	TiO ₂	1.4%
Iron Oxide	Fe ₂ O ₃	2.6%
Other		3.5%

NOTE: The information contained in this bulletin is believed to be accurate and reliable but is not to be construed as implying any warranty or guarantee of performance. Data are subject to reasonable variations and should not be used for specification purposes.

REV. 10/17 DSP

Trademarks

Registered trademarks contained in this document are owned by Knight Material Technologies in the United States and may be registered in other jurisdiction, unless otherwise stated. Refer to our website for trademark details: www.knightmaterials.com.

©2021 Knight Material Technologies - All Rights Reserved

5385 Orchard View Drive S.E. · P.O. Box 30070
 East Canton, Ohio USA 44730
 Phone: +1 (330) 488-1651
 Email: sales@knightmaterials.com
www.knightmaterials.com